

StanChem, Inc.
401 Berlin Street, East Berlin, CT 06023
(860) 828-0571
Fax (860) 828-3297

- Specialty Coatings
- Albi Fireproofing
- Latex Polymers

StanChem, Inc.

STANCHEM 6495

DESCRIPTION:

StanChem 6495 is an acrylic copolymer emulsion that after drying, cross-links at 300 - 325 °F for textile printing applications. SC 6495 exhibits excellent solvent resistance and soft hand.

PRODUCT DATA:

Typical Physical Properties:

Type:	Acrylic Copolymer
Solids by weight:	40.0 - 42.0 %
Viscosity @ 25° C: Brookfield RVT #4 @ 20 RPM	< 200 cps
pH @ 25° C:	2.0 – 3.0
Free Monomer:	0.1 % maximum
Weight/gallon:	8.8 +/- 0.10lbs.
Ionic Charge:	Nonionic
Tg °C: (DSC)	-7

WARRANTY:

Seller warrants that its product will meet the specifications which it sets for them. Seller's responsibility under this warranty will be limited solely to replacing the products which prove defective, provided that the Buyer gives Seller prompt notice in writing of said defect. Products may be returned to Seller only after written authorization has been obtained from Seller. The foregoing warranty is in lieu of all other warranties, whether oral, written, express, implied or statutory. IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE WILL NOT APPLY. Technical or other advice is furnished by us solely as an accommodation and shall not increase the scope of our responsibilities or liability. Seller's warranty obligations and Buyer's remedies hereunder are solely and exclusively as stated herein: In no event will Seller be liable either for the labor and other associated costs incurred in replacing the product, including, but not limited to, its removal and application, or for other incidental or consequential damages.