

## StanChem SC 6763

---

### Description:

**StanChem SC 6763** is a medium hand, 100% acrylic emulsion. SC 6763 provides outstanding durability to washing and dry cleaning when used in textile coatings.

---

### Typical Physical Properties:

<b>Type:</b>	Acrylic Copolymer Emulsion
<b>Solids by weight:</b>	40.0 – 42.0 %
<b>Viscosity* @ 25° C:</b>	<100 cps
<b>pH @ 25°C:</b>	6.5 – 8.5
<b>Density:</b>	8.50 ± 0.10 lbs/gal
<b>Tg (calc.)</b>	-30°C
<b>Free Monomer:</b>	0.1 % maximum
<b>Mullen Burst<sup>1</sup> results:</b>	55-60 psi (dry) 18-22 psi (wet)

<sup>1</sup>Dry Procedure: – 1 gram (4"x4") of 14 lb paper is saturated in a 10% solids polymer solution, with a target saturation of 15-30%. Specimen is then cured for 7 minutes at 350°F before testing. Wet procedure is same, but includes a 10 minute water soak before testing.

\*Brookfield RVT, #4 Spindle @ 20 RPM

**Storage:** **SC 6763** is stable for at least 12 months from manufacturing date when stored between 5°C-40°C in appropriate containers.

### WARRANTY:

Seller warrants that its product will meet the specifications which it sets for them. Seller's responsibility under this warranty will be limited solely to replacing the products which prove defective, provided that the Buyer gives Seller prompt notice in writing of said defect. Products may be returned to Seller only after written authorization has been obtained from Seller. The foregoing warranty is in lieu of all other warranties, whether oral, written, express, implied or statutory. IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE WILL NOT APPLY. Technical or other advice is furnished by us solely as an accommodation and shall not increase the scope of our responsibilities or liability. Seller's warranty obligations and Buyer's remedies hereunder are solely and exclusively as stated herein: In no event will Seller be liable either for the labor and other associated costs incurred in replacing the product, including, but not limited to, its removal and application, or for other incidental or consequential damages.