

StanChem SC 6872

Description:

StanChem SC 6872 is a crosslinking acrylic polymer, with utility in a variety of textile and non-woven applications. It can be used to impart firmness of hand to a broad range of textile and non-woven applications.

Typical Physical Properties:

Type: Crosslinkable Acrylic

Solids by Weight: 46.0 - 48.0 %

Viscosity* @ 25°C: <600 cps

pH @ 25°C: 8.0 – 9.0

Density: 9.0 ± 0.10 lbs./gal

Tg (DSC, Midpoint) 42°C

Freeze / Thaw PASS (5 Cycles)
Resistance (10°F)

Mullen Burst¹ results: 73-80 psi (dry)

32-38 psi (wet)

¹Dry Procedure: – 1 gram (4"x4") of 14 lb paper is saturated in a 10% solids polymer solution, with a target saturation of 15-30%. Specimen is then cured for 7 minutes at 350°F before testing. Wet procedure is same, but includes a 10 minute water soak before testing.

Storage: SC 6872 is stable for at least 12 months from manufacturing date when stored between 5°C-40°C in appropriate containers.

WARRANTY:

Seller's responsibility under this warranty will be limited solely to replacing the products which prove defective, provided that the Buyer gives Seller prompt notice in writing of said defect. Products may be returned to Seller only after written authorization has been obtained from Seller. The foregoing warranty is in lieu of all other warranties, whether oral, written, express, implied or statutory. IMPLIED WARRANTIES OF MERCHANTINILITY AND FITNESS FOR A PARTICULAR PURPOSE WILL NOT APPLY. Technical or other advise is furnished by us solely as an accommodation ands shall not increase the scope of our responsibilities or liability. Seller's warranty obligations and Buyer's remedies hereunder are solely and exclusively as stated herein: In no event will Seller be liable either for the labor and other associated costs incurred in replacing the product, including, but not limited to, its removal and application, or for other incidental or consequential damages.

^{*}Brookfield RVT, #1 Spindle @ 60 RPM